

Description	Scorex® is a blast furnace grit made of iron furnace slag from Voestalpine, also called «calcium silicate».																								
Applications	Blastcleaning of steel and stone/concrete surfaces, removal of mill scale, rust, old paint, dirt, etc. Suitable for SA-3, SA-2½, SA-2 as well as sweep blasting SA-1																								
Properties	<table border="0"> <tr><td>Shape</td><td>:</td><td>sharp and angular</td></tr> <tr><td>Colour</td><td>:</td><td>light brown</td></tr> <tr><td>Hardness</td><td>:</td><td>6 – 7 Mohs</td></tr> <tr><td>Specific density</td><td>:</td><td>2,3-2,6 kg/dm³</td></tr> <tr><td>Loose bulk density</td><td>:</td><td>1,3-1,4 kg/dm³</td></tr> <tr><td>Conductivity</td><td>:</td><td>less than 25 mS/m</td></tr> <tr><td>Eater-soluble chlorides</td><td>:</td><td>less than 0.0025% (m/m)</td></tr> </table>	Shape	:	sharp and angular	Colour	:	light brown	Hardness	:	6 – 7 Mohs	Specific density	:	2,3-2,6 kg/dm ³	Loose bulk density	:	1,3-1,4 kg/dm ³	Conductivity	:	less than 25 mS/m	Eater-soluble chlorides	:	less than 0.0025% (m/m)			
Shape	:	sharp and angular																							
Colour	:	light brown																							
Hardness	:	6 – 7 Mohs																							
Specific density	:	2,3-2,6 kg/dm ³																							
Loose bulk density	:	1,3-1,4 kg/dm ³																							
Conductivity	:	less than 25 mS/m																							
Eater-soluble chlorides	:	less than 0.0025% (m/m)																							
Chemical Composition (Indication)	<table border="0"> <tr><td>SiO₂</td><td>:</td><td>35 - 40 %</td><td><1% free silica</td></tr> <tr><td>CaO</td><td>:</td><td>33 - 38 %</td><td></td></tr> <tr><td>MgO</td><td>:</td><td>9 - 15 %</td><td></td></tr> <tr><td>Al₂O₃</td><td>:</td><td>6 - 10 %</td><td></td></tr> <tr><td>FeO</td><td>:</td><td>0,4 - 0,6 %</td><td></td></tr> <tr><td>Other</td><td>:</td><td>traces only</td><td></td></tr> </table>	SiO ₂	:	35 - 40 %	<1% free silica	CaO	:	33 - 38 %		MgO	:	9 - 15 %		Al ₂ O ₃	:	6 - 10 %		FeO	:	0,4 - 0,6 %		Other	:	traces only	
SiO ₂	:	35 - 40 %	<1% free silica																						
CaO	:	33 - 38 %																							
MgO	:	9 - 15 %																							
Al ₂ O ₃	:	6 - 10 %																							
FeO	:	0,4 - 0,6 %																							
Other	:	traces only																							
Particle Sizes	<table border="0"> <tr><td>SC250</td><td>0,1 - 0,315 mm</td></tr> <tr><td>SC06</td><td>0,2 - 0,6 mm</td></tr> <tr><td>SC08</td><td>0,2 - 0,8 mm</td></tr> <tr><td>SC15</td><td>0,2 - 1,5 mm</td></tr> <tr><td>SCX</td><td>0,5 - 1,6 mm</td></tr> <tr><td>SC25</td><td>0,2 - 2,5 mm</td></tr> <tr><td>SCST</td><td>0,5 - 2,5 mm</td></tr> </table>	SC250	0,1 - 0,315 mm	SC06	0,2 - 0,6 mm	SC08	0,2 - 0,8 mm	SC15	0,2 - 1,5 mm	SCX	0,5 - 1,6 mm	SC25	0,2 - 2,5 mm	SCST	0,5 - 2,5 mm										
SC250	0,1 - 0,315 mm																								
SC06	0,2 - 0,6 mm																								
SC08	0,2 - 0,8 mm																								
SC15	0,2 - 1,5 mm																								
SCX	0,5 - 1,6 mm																								
SC25	0,2 - 2,5 mm																								
SCST	0,5 - 2,5 mm																								
Packaging	<ul style="list-style-type: none"> - 3-ply paperbags of 25 kg, on shrinkfoiled export pallets. - Strong woven propylene big bags with 4 lifting loops of 1.500 kg - Other packaging options on request 																								
ISO	Product standards ISO 11126-6 und 11127																								

Please contact us for more information:

Worldwide

Tel: +49 (0)40 781298-0
abrasives@sibelco.com

www.sibelco.eu

Sibelco Deutschland GmbH

Müggelburger Straße 10
DE- 20539 Hamburg
GERMANY

